

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 64-037832

(43)Date of publication of application : 08.02.1989

(51)Int.Cl.

H01L 21/205

(21)Application number : 62-193733

(71)Applicant : FUJITSU LTD

(22)Date of filing : 04.08.1987


(72)Inventor : OTSUKA NOBUYUKI
OZEKI MASASHI
MOCHIZUKI KOJI

(54) METHOD OF GROWING COMPOUND SEMICONDUCTOR CRYSTAL

(57)Abstract:

PURPOSE: To form a compound semiconductor crystal in an epitaxial manner by a method wherein an inert gas is used as a carrier, a source-gas composed of a compound containing a methyl group is flowed, the film of an element as the component of a source is shaped, the source-gas is stopped, the gas of another compound is flowed and the film of an element as a component is formed.

CONSTITUTION: When a GaAs single crystal is grown onto a GaAs single crystal substrate by utilizing an atomic layer epitaxial method, N₂ gas is used as a carrier, and (CH₃)₃Ga is employed as a Ga source and AsH₃ as an As source. The substrate is brought to 500° C and a bubbler to 3° C. The flow rate of (CH₃)₃Ga is brought to 40cm³/min at 0° C and 1 atm. to shape the monoatomic layer of Ga, and the feed of (CH₃)₃Ga is stopped. AsH₃ is flowed at the flow rate of 480cm³/min at 0° C and 1 atm. to form the monoatomic layer of As, and a GaAs single crystal layer is shaped in an epitaxial manner. Since an inert gas is used as the carrier, there is no possibility of the promotion of thermal decomposition, thus largely improving controllability at the time of crystal growth.



LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]